

Ce tableau indique la solidité des couleurs (SC) par couleur de feutre de laine selon le test ISO 105 B02. L'échelle va de 1 à 8, 8 étant le maximum.

couleur	SC
1	7 - 8
2	7
3	7
4	5
5	4 - 5
6	7
7	7 - 8
8	7
9	6 - 7
10	6
11	6
12	7
13	5 - 6
14	6
15	5 - 6
16	6
17	6 - 7
18	5 - 6
19	6 - 7
20	7 - 8
21	8
22	7 - 8
23	8
24	4 - 5
25	3 - 4
26	4
27	3
28	4
29	4
30	4 - 5
31	4
32	3 - 4
33	5

couleur	SC
34	4
35	5 - 6
36	6
37	6 - 7
38	4
39	5
40	7
41	6
42	3 - 4
43	3
44	6
45	6
46	6 - 7
47	6
48	6
49	5 - 6
50	5
51	4 - 5
52	3 - 4
53	3
54	3 - 4
55	6 - 7
56	4 - 5
57	6
58	4
59	5 - 6
60	5
61	4 - 5
62	4
63	4 - 5
64	4 - 5
65	6
66	7 - 8

couleur	SC
67	7 - 8
68	6
69	5 - 6
70	7
71	3 - 4
72	3 - 4
73	5
74	7 - 8
75	5 - 6
76	3
77	3
78	4
79	5 - 6
80	
81	
82	
83	
84	
85	
86	
87	
88	
89	
90	
91	6 - 7
G-000	6
G-00	6
G-0	6
G-1	6
G-2	6
G-3	6
G-4	6
G-5	6

couleur	SC
G-6	6
G-7	6
G-8	6
G-9	6
G-002	7
G-003	7
G-018	5 - 6
G-033	5
G-042	3 - 4
G-075	5 - 6
G-077	3
G-130	7
G-150	6 - 7
G-448	6
G-484	7
G-539	6 - 7
G-555	6
G-645	6
G-732	6
G-800	7 - 8
G-801	7